



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁶ : B32B 5/28, 27/18, H05K 1/03, C01F 7/02		A1	(11) International Publication Number: WO 98/31538
			(43) International Publication Date: 23 July 1998 (23.07.98)
(21) International Application Number: PCT/EP98/00211 (22) International Filing Date: 15 January 1998 (15.01.98) (30) Priority Data: 9700708.2 15 January 1997 (15.01.97) GB (71) Applicant (for all designated States except US): MARTIN-SWERK GMBH FÜR CHEMISCHE UND METALLURGISCHE PRODUKTION [DE/DE]; Kölner Strasse 110, D-50126 Bergheim (DE). (72) Inventors; and (75) Inventors/Applicants (for US only): BROWN, Neil [GB/DE]; Buchenweg 1, D-50126 Bergheim (DE). AGGLETON, Michael [GB/GB]; 72 Millfields, Hucclecote, Gloucester GL3 3NM (GB). (74) Agents: WEINHOLD, Peter et al.; Kuhnert, Wacker & Partner, Alois-Steinecker-Strasse 22, D-85354 Freising (DE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	

(54) Title: LAMINATE FOR PRINTED CIRCUIT BOARDS

(57) Abstract

The present invention relates to printed circuit board laminates which are characterized by improved thermal stability. The improved properties are attributed to the use of a novel aluminium hydroxyde which is described by the molecular representation: $\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$ where $n > 2.6$ and < 2.9 .

- dH/dT



Temperature (°C)

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Laminate for printed circuit boards

The present invention relates to a thermally stable fire retardant laminate for printed circuit boards using a thermally stable aluminium hydroxide without the need for other fire retardant agents.

- 5 Printed circuit board laminate types are defined by the American NEMA (National Electrical Manufacturers Association) standard, the terminology is accepted world-wide. Generally, laminates are categorized according to the type of reinforcement used, i. e., cellulose paper or glass. Typically, the type FR-2 uses paper only, CEM-1 uses paper and woven glass, while type CEM-3 contains both woven and non-woven glass. The type FR-4
10 contains woven glass only.

To achieve the required V0 level of fire retardancy according to American Underwriters Laboratories' standard UL-94, it is necessary to add either fire retardant chemicals to the polymer system or build halogens or phosphorous into the backbone of the polymer itself.

- 15 On combustion, these additives help to extinguish the fire. However, in the process of doing so they produce toxic and corrosive gases. In the case of combustion of FR-2 laminates, which contain phosphorous compounds, phosphoric acid is formed. CEM-1, CEM-3 and FR-4 laminates which contain brominated epoxy resin, produce corrosive and toxic hydrogen bromide on combustion.

20

It is well known in the art that aluminium hydroxide may be used to improve the fire retardancy of synthetic polymer systems based on for example epoxy, polyester, and vinyl ester because the polymers decompose in the same temperature range as the aluminium hydroxide. However, the thermal stability of the gibbsite form of aluminium hydroxide
25 ($\text{Al}(\text{OH})_3$ or sometimes represented as $\text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$) is insufficient at the temperatures used to solder components to a printed circuit board laminate. This can result in blistering of the laminate thereby rendering it unusable.

- It is known that when gibbsite type aluminium hydroxide is heat treated in air it is partially
30 converted to the mono hydrate form, boehmite (AlOOH or $\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$) which improves thermal stability but to the detriment of fire retardancy.

Japanese patent disclosure JP-A 60/203 438 describes a CEM-3 laminate containing heat treated gibbsite type aluminium hydroxide which has improved thermal stability over standard aluminium trihydroxide but which does not give the required level of fire retardancy so that brominated epoxy resin has to be used to achieve the UL 94 V0 rating. In such circumstances, and in the absence of superior fire properties, other inorganic materials such as talc or clay could also be used.

The object of the present invention is to produce a CEM-3 laminate which has good thermal stability, is halogen/phosphorous free and meets the UL 94 V0 requirement. A further object of the invention is to develop a thermally stable aluminium hydroxide which impart the required characteristics to the laminate.

It was possible to achieve the object of the invention by means of a laminate for printed circuit boards according to claim 1, by a method for the preparation of the laminate according to claim 7, by a printed circuit board made of the laminate according to claim 13 by a thermally stable aluminium hydroxide according to claim 16.

The CEM-3 type laminates are as a rule constructed from two layers of woven fibreglass on the outsides and three layers of non-woven glass tissue in the core. According to claim 1 of the invention, the laminate for printed circuit boards has surface layers comprising curable resin-impregnated woven glass fabric and intermediate layers comprising curable resin-impregnated non-woven glass, and is characterized in that the intermediate layers contain 200 % by weight to 275 % by weight (based on the resin) of a thermally stable aluminium hydroxide of the molecular formula $Al_2O_3 \cdot nH_2O$ wherein n has a value >2.6 to <2.9 .

25

The curable resin may be an unsaturated polyester resin, an epoxy, a vinyl ester or any suitable thermosetting compound which on combustion decomposes in the same temperature range as the thermally stable aluminium hydroxide.

The laminates may be based on epoxy resin which allows a batch process to be used. The laminates may also be produced by continuous process using unsaturated polyester or vinyl

ester, i. e., resins which polymerize via a free radical mechanism. The nature of the invention however does not limit the manufacturing technique for the laminate.

When the production of the laminate is based on epoxy resin, as a rule two layers of woven glass preimpregnated with the epoxy resin are combined with three layers of non-woven glass preimpregnated with epoxy resin containing thermally stable aluminium hydroxide. These five layers are usually then combined with one or two layers of copper foil on the outside and the assembly subjected to heat and pressure to polymerize the resin and consolidate the laminate.

Most epoxy resins used for electrical and electronic applications are derived from bisphenol A or cycloaliphatic species. The most common curing agent is dicyandiamide.

According to the method of the present invention, the intermediate layer comprising curable resin impregnated non-woven glass contain 200 % by weight to 275 % by weight, preferably 225 % by weight to 250 % by weight, of the thermally stable aluminium hydroxide relative to the weight of the curable resin.

In the molecular formula, $\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$, n preferably has a value of 2.7 to 2.8.

A feature of the halogen and phosphorous free epoxy laminate of the present invention is the use of thermally stable aluminium hydroxide as the sole fire retardant.

The prior art describes the removal of a part of the water content of aluminium hydroxide as a means of improving its thermal stability. If insufficient water is removed, the laminate containing the aluminium hydroxide does not survive the soldering operation. However, a limitation of the prior art is that if too much water is removed the resulting aluminium hydroxide may contain too little water of constitution to act effectively as a fire retardant.

A further complication is the formation of the more thermally stable phase aluminium hydroxide (boehmite), which not only contains one third of the amount of water as the

original aluminium trihydroxide (gibbsite) it also holds it back to 520 °C before releasing it. This detracts further from fire retardant effectiveness.

It is well known in the art that the finer is the aluminium hydroxide starting material, the less is the tendency to form the undesirable boehmite phase on heating. However, at the particle sizes necessary to avoid boehmite formation ($<1\text{ }\mu\text{m}$), it becomes virtually impossible to process the material in synthetic resin. On the other hand, thermally stable aluminium hydroxide which is processable will contain too much boehmite thus preventing the production of a halogen-free epoxy laminate which passes UL 94 V0.

10

Essentially, the novel feature of the thermally stable aluminium hydroxide of the present invention is the surprisingly low boehmite content relative to the average particle size. This allows lower values of n to be obtained thereby improving water stability without compromising on fire properties' effectiveness. Thus, for $n < 2.6$, there is insufficient water (and too much boehmite) to achieve the required fire properties whereas for $n > 2.9$, there is too much water still present to achieve the required thermal resistance to soldering.

15

The decoupling of the relationship between boehmite formation and particle size is achieved by suitable mechanical treatment of relatively coarse particles (average size ca. 60 μm) of aluminium hydroxide prior to the thermal pretreatment step. A suitable mechanical treatment would be provided for example by the application of compressive forces to aluminium hydroxide to increase polycrystallinity. Without being bound to any particular theory, it appears that structural degradation by such means creates the conditions for a more easy diffusion of water to the exterior of the crystals thereby minimizing the tendency to build-up of hydrothermal pressure within the crystals and hence the reduced tendency to boehmite formation.

20

25

In practical terms, the product of the invention can be created by a size reduction of an aluminium hydroxide agglomerate with an average particle size $D_{50\%}$ of 40 to 80 μm , preferably of 50 to 70 μm , crystallized out from a typical Bayer process - sodium aluminate solution.

30

Any size reduction technique, e.g. ball milling, which separates the crystals present within coarser agglomerates with little or no gross fracture of the single crystals can be applied. A simultaneous broadening of the particle size distribution due to attrition and the absence of crystal breakage by gross fracture improves the processability of the thermally stable
5 aluminium hydroxide in the respective resin system.

The subsequent thermal stabilization can be achieved by simply heating the material recovered from the size reduction treatment at a temperature and during a time sufficient to reduce the water loss on ignition from 34.5 wt.% ($n = 3$) to a level corresponding to the n
10 value according to the invention.

The thermally stable aluminium hydroxide according to the present invention expediently has a specific surface area measured according to the BET method of from 2 to 10 m²/g. A very essential point is the particle size distribution which combines a relatively fine average
15 size with a breadth of particle sizes. this improves the dispersion of the thermally stable aluminium hydroxide in the resin while at the same time minimizing the tendency of the coarser particles to sediment out during processing and avoiding any filtering effects by the non-woven glass. an optimum particle size distribution allow minimum viscosity of the resin/filler mix at a filling level sufficiently high to achieve the desired flame retardant
20 properties of the laminate without the need to add any other flame retardants.

The average particle size of the thermally stable aluminium hydroxide of the present invention D50% is in the range 5 to 10 µm. The breadth of the particle size distribution is indicated by the D10% range, i. e., 10 % by weight of the particles are smaller than 0.5 to
25 1.5 µm and the D90% range, i. e., 90 % by weight of the particles are less than 20 to 35 µm in size.

The oil absorption measured according to standard method DIN 53199 is within the range 25 to 35 ml/100 g.

30

The incorporation of the thermally stable aluminium hydroxide into the curable resin can be accomplished by methods known to those skilled in the art, i. e., usually by introducing the

filler into the predissolved mixture of resin and curing agent using suitable equipment such as shearing head mixer. If needed, other inorganic thermally stable fillers may be added to the formulation such as fine silica, clay or talc, although none of these would significantly enhance fire properties.

5

Further processing of the resin / filler mix to the "prepreg" stage and then to the cured laminate is common state of the art and described in the literature, an example of which is "Handbook of Epoxide Resins", published by the McGraw-Hill Book Company.

- 10 The cured laminate according to the present invention shows excellent thermal stability; when immersed in molten solder at 260 °C, it shows no signs of blistering or bubbling for a period of over 90 seconds. The laminate also has excellent fire retardancy characteristics and meets the requirements of UL 94 V-0.

15 Figures:

Figure 1 shows the effect of heating aluminium hydroxides of different particle sizes (based on the measurement of the "loss on ignition, LOI") on the percent of boehmite (AlOOH) formed by X-ray diffraction.

20

Curves 1 to 3 designate standard aluminium hydroxides (Martinal[®] ON-types of Martinswerk GmbH, Bergheim, Germany) with the particle sizes 60 μm (ON, curve 1), 10 μm (ON-310, curve 2) and 1.5 μm (OL-104, curve 3) in comparison with the thermally stable aluminium hydroxide of the invention (curve 4).

25

Figure 2 shows differential scanning calorimetry of the thermally stable aluminium hydroxide of the invention (curve 1) in comparison with a standard aluminium hydroxide (Martinal[®] ON-310 of Martinswerk GmbH, Bergheim, Germany).

Examples:

Fine crystals of aluminium hydroxide (average size 1 - 2 μm) are agglomerated to ca. 60 μm average size by using a seed charge of 50 kg/dm^3 sodium aluminate solution of
5 following concentration: Na_2O - 140 kg/dm^3 , Al_2O_3 - 150 kg/dm^3 , total Na_2O - 150 kg/dm^3 . The working capacity of the crystallizer was 1 m^3 . Crystallization temperature was 75°C with a retention time of 24 h.

Alumina liquor productivity was ca. 40 kg/dm^3 . The product of crystallization was washed with deionized water and dried at 105°C for 4 h.

10

Size reduction of the aluminium hydroxide particles was effected by means of a vibration mill (type Palla 200 of the KHD company). The milling conditions were as follows: motor - 1000 rpm; loading of cylpebs - ca. 65 % by volume; cylpebs dimensions - 12 mm x 12 mm aluminium oxide; mill throughput ca. 50 kg/h. Under these conditions, the feed aluminium
15 hydroxide was reduced in size to the dimensions given in Table 1.

The final step of thermal stabilization was achieved by lowering the water loss on ignition from the 34.5 wt.% of the size reduced material to ca. 31 wt.% by heating in an electric oven operating at a temperature of 220°C for a time of ca. 2h. The properties of the
20 thermally stable material are also given in Table 1.

The physical properties of the aluminium hydroxide according to the present invention are shown in comparison to a standard aluminium hydroxide of Martinswerk GmbH, Bergheim, Germany and heat treated aluminium hydroxide of the prior art as described in JP-A 60 /
25 203 438.

Table 1

Characteristics of the thermally stable aluminium hydroxide in comparison with standard aluminium hydroxide (Martinal[®] ON-310, Martinswerk GmbH, Bergheim, Germany) and
30 thermally stable aluminium hydroxide of the prior art (JP-A 60 / 203 438)

Physical Parameter	Aluminium Hydroxide of the Invention	Standard Aluminium Hydroxide	Aluminium Hydroxide of the prior art
$\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$ "n"	2.7	3.0	2.4
Particle size D10% (μm)	1.0	2.0	0.6
Particle size D50% (μm)	7.5	10.0	1.0
Particle size D90% (μm)	28.0	20.0	1.8
Specific Surface Area m^2/g	6.0	2.5	50.0
Oil Absorption (ml/100 g)	28.0	27	33.0

Differential scanning calorimetry shows the virtual absence of any endotherm due to boehmite compared to the standard aluminium hydroxide as represented by Martinal® ON-310 (see Figure 2).

Batch Process

100 parts of an epoxy resin with epoxy equivalent of 400 - 500 (DOW DER 652) dissolved in 30 parts of acetone is mixed with 4 parts of dicyandiamide predissolved in 36 parts of 2-methoxy ethanol. To this mix is added 0.1 parts of 2-methyl imidazole to accelerate the resin cure (Mix A).

Woven glass fabric (style 7628 manufactured by Interglass) is impregnated with the Mix A to a resin content of 42 %, and the resin B-staged for 2 min. at 160 °C to produce a dry prepreg.

Separately, to Mix A is added 250 phr (i. e., parts per hundred resin) of the different types of aluminium hydroxide shown in Table 2. Each of these mixes are impregnated into non-woven glass (type E 105 manufactured by Owens Corning) to give weight corresponding to 90 % of the total. The aluminium hydroxides are predispersed in an amount of acetone commensurate with achieving the final mix viscosity. The resin system is then B-staged for 3 min. at 160 °C to produce a dry, handlable prepreg.

Three of the non-woven glass prepreg layers are sandwiched between two woven glass prepreg layers. This assembly has copper foil placed on both sides and the pack laminated at 180 °C at a pressure of 50 bar for 90 min. to produce a copper clad laminate 1.6 mm thick.

Continuous Process

In the above example, the epoxy resin may be replaced by resin systems which cure by a free radical polymerization reaction thereby leading to a negligible level of volatile emissions. Examples of these are unsaturated polyester, epoxy acrylate or vinyl ester resins.

In the continuous process, the woven glass cloth (style 7628, Interglass) is impregnated continuously through, e. g., a liquid vinyl ester resin (DOW Derakane) containing 100 parts by weight of resin and 1.5 parts of benzoyl peroxide. Separately, the non-woven glass is impregnated continuously through vinyl ester / benzoyl peroxide mix containing 250 phr of the aluminium hydroxide of the present invention.

After initial curing in a tunnel oven for 10 min. at 120 °C, the layers are combined with two layers of copper foil on the outside and the seven layers consolidated under heat and pressure in a conveyorised moving platform for 15 min. at 150 °C. The continuous laminate so produced has a thickness of 1.6 mm.

30

Test Results

The thermal stability and fire retardant properties of the laminates produced by these techniques are dependent on the properties and level of the aluminium hydroxide, not on the
5 polymer nor laminate manufacturing technique.

In Table 2 are given the results obtained when using non-halogenated epoxy resin. These should be taken as typical and representative of all of the polymer types described.

- 10 Comparison is made between the thermally stable aluminium hydroxide of the invention and the standard aluminium hydroxide (Martinal[®] ON-310 of Martinswerk GmbH, Bergheim, Germany) and thermally stable aluminium hydroxide of the state of the art (JP-A 60/203 438).
- 15 Solder resistance is measured by fully immersing the laminate in molten solder at 260 °C. When the aluminium hydroxide starts to decompose it is possible to hear the laminate blistering and the escaping water causes "waves" at the solder surface. The time is measured until the blistering / waves are detected.
- 20 The flammability is defined by the American Underwriters Laboratory UL 94 standard which categorizes performance on combustion as V-0 (the best), V-1 and HB (the worst). For pcb applications laminates have to meet the V-0 category.

Table 2

Solder Resistance and Flammability Test Results

Test	Laminate with Aluminium Hydroxide of the Invention	Laminate with Standard Aluminium Hydroxide	Laminates with Aluminium Hydroxide of the Prior Art	
value of "n"	2.7	3.0	2.9	2.4
Aluminium Hydroxide	250 phr	250 phr	250 phr	250 phr
Solder Resistance	>90 s	20 s	20 s	>90 s
Flammable UL 94	V0	V0	V0	HB

Claims:

1. Laminate for printed circuit boards having surface layers comprising resin impregnated woven glass fabric and intermediate layers comprising curable resin impregnated non-woven glass, characterized in that the intermediate layer contains 200 % by weight to 275 % by weight based on the resin in the intermediate layer of aluminium hydroxide of the molecular formula $\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$ wherein n has a value of >2.6 to <2.9 .
5
2. Laminate according to claim 1, wherein the thermally stable aluminium hydroxide has a specific surface area measured by the BET method of 2 to $10 \text{ m}^2/\text{g}$.
10
3. Laminate according to claim 1 or 2, wherein the thermally stable aluminium hydroxide has a particle size in the D50% range of 5 to $10 \mu\text{m}$.
- 15 4. Laminate according to one of the claims 1 to 3, wherein the thermally stable aluminium hydroxide has a particle size in the D10% range of 0.5 to $1.5 \mu\text{m}$ and in the D90% range of 20 to $35 \mu\text{m}$.
5. Laminate according to one of the claims 1 to 4, wherein the thermally stable aluminium hydroxide has an oil absorption of 25 to 35 ml/100 g.
20
6. Laminate according to one of the claims 1 to 5, wherein as a curable resin an unsaturated polyester resin, an epoxy or a vinyl ester is applied.
- 25 7. Method for the preparation of a laminate for printed circuit boards by composing together surface layers comprising curable resin impregnated woven glass fabric and intermediate layers comprising curable resin-impregnated non-woven glass, characterized in that the curable resin-impregnated non-woven glass contains 200 % by weight to 275 % by weight based on the resin in the intermediate layers of a thermally stable aluminium hydroxide of the molecular formula $\text{Al}_2\text{O}_3 \cdot n\text{H}_2\text{O}$, wherein n has a value of >2.6 to <2.9 .
30

8. Method according to claim 7, wherein the thermally stable aluminium hydroxide has a specific surface area measured by the BET method of 2 to 10 m²/g.
9. Method according to claim 7 or 8, wherein the thermally stable aluminium hydroxide has a particle size in the D50% range of 5 to 10 µm.
10. Method according to one of the claims 7 to 9, wherein the thermally stable aluminium hydroxide has a particle size in the D10% range of 0.5 to 1.5 µm and in the D90% range of 20 to 35 µm.
11. Method according to one of the claims 7 to 10, wherein the thermally stable aluminium hydroxide has an oil absorption of 25 to 35 ml / 100 g.
12. Method according to one of the claims 7 to 11, wherein as a curable resin an unsaturated polyester resin, an epoxy or a vinyl ester is applied.
13. Printed circuit board made of a laminate according to claims 1 to 6, or prepared following a method according to claims 7 to 12.
14. Thermally stable aluminium hydroxide of the molecular formula Al₂O₃.nH₂O, wherein n has a value of >2.6 to <2.9.
15. Thermally stable aluminium hydroxide according to claim 14 having specific surface area measured by the BET method of 2 to 10 m²/g.
16. Thermally stable aluminium hydroxide according to claim 14 or 15 having a particle size in the D50% range of 5 to 10 µm.
17. Thermally stable aluminium hydroxide according to one of the claims 14 to 16 having a particle size in the D10% range of 0.5 to 1.5 µm and in the D90% range of 20 to 35 µm.

18. Thermally stable aluminium hydroxide according to one of the claims 14 to 17 having an oil absorption of 25 to 35 ml/100 g.

1/2




FIGURE 1

2/2


 $-\text{dH}/\text{dT}$ 

FIGURE 2

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/00211

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B32B5/28 B32B27/18 H05K1/03 C01F7/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B32B C01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 017, no. 013 (E-1304), 11 January 1993 & JP 04 243185 A (KANEKAFUCHI CHEM IND CO LTD), 31 August 1992, see abstract	1-18
A	DATABASE WPI Section Ch, Week 8547 Derwent Publications Ltd., London, GB; Class A21, AN 85-293904 XP002065735 & JP 60 203 438 A (SUMITOMO BAKELITE CO) see abstract	1, 14
	-/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

25 May 1998

Date of mailing of the international search report

22/06/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ibarrola Torres, O

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/00211

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CHANAKYA MISRA: "Industrial Alumina Chemicals" AMERICAN CHEMICAL SOCIETY MONOGRAPH 184, 1986, WASHINGTON, DC, XP002065734 see page 83 - page 85 ---	14
X	DATABASE WPI Section Ch, Week 7640 Derwent Publications Ltd., London, GB; Class A60, AN 76-74517X XP002065736 & JP 51 027 898 A (SHOWA DENKO KK) see abstract ---	14
A	EP 0 118 031 A (VAW VER ALUMINIUM WERKE AG) 12 September 1984 see the whole document ---	14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/00211

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0118031 A	12-09-1984	DE 3308023 A	13-09-1984
		JP 59168041 A	21-09-1984